

Mechanistic Understanding of Sputtering

Ashwini Kumar^{1,2,*}, Gong Yong^{1,2,*}

¹*School of Electrical and Electronics Engineering, Luzhou Vocational and Technical College, Luzhou, Sichuan, China*

²*Luzhou Key Laboratory of Intelligent Control and Applications Technology of Electronic Devices, Luzhou, Sichuan, China*

*Corresponding authors: kumar1984@lzy.edu.cn, gongyong@lzy.edu.cn

1.1 Introduction

Sputtering is among the most fundamental and widely used physical processes in material modification, thin-film deposition, and surface engineering. Broadly defined, sputtering is the ejection of atoms or molecules from a solid surface when it is bombarded by energetic ions or particles. These ejected species can either escape into the vacuum or redeposit onto nearby substrates to form thin films. As a versatile and controllable technique, sputtering underpins many modern technologies, ranging from semiconductor device fabrication through nanostructure engineering to advanced functional coatings. Understanding the mechanisms that govern sputtering is essential not only for optimizing deposition processes but also for tailoring materials at the atomic scale. At its core, sputtering involves momentum transfer from incident energetic ions (often noble gas ions such as Ar^+ or Kr^+) to atoms in a solid target, leading to the ejection of surface atoms. The threshold condition for sputtering requires that the incident ions have sufficient energy to overcome the surface binding energy of atoms in the target material [1]. Unlike simple evaporation, sputtering is a nonequilibrium process driven by particle bombardment, resulting in unique energy and angular distributions of the emitted atoms. The sputtering yield—defined as the average number of atoms ejected per incident ion—depends on various factors, including ion energy, incident angle, ion mass, and the binding energy of the target atoms [2]. Since the sputtering mechanism imposes no basic restriction on the nature of the target material, it can be applied to metals, semiconductors, insulators, and even composite or multicomponent systems. This universality makes it an indispensable tool in the technology of thin films.

1.1.1 Historical Development of Sputtering Techniques

Sputtering was first noticed in the middle of the nineteenth century. Grove [3] noticed the erosion of cathodes during the gas discharge, and this was later recognized as sputtering. The early works were largely qualitative and related to cathode erosion during glow discharges. Systematic studies became possible with the advent of vacuum technology and electron microscopy during the twentieth century. The first important theoretical steps were made by Thompson (1968), who estimated the energy distribution, and by Sigmund (1969) [1], who proposed a collision cascade model serving up to now as the basis of the sputtering theory. Experimental measurements of the sputtering yield, performed during the 1960s and 1970s, allowed validation and refinement of these models [4]. Technological development followed closely. By the 1970s, magnetron sputtering emerged as a breakthrough, introducing magnetic confinement of plasma electrons to enhance ionization efficiency and deposition rates [5]. Radio-frequency (RF) sputtering allowed deposition of insulating materials, while reactive sputtering enabled the formation of compound films such as oxides and nitrides [6]. More recently, high-power impulse magnetron sputtering (HiPIMS) has been developed, offering high ionization of sputtered material and improved film properties [7]. Thus, the history of sputtering reflects a dynamic interplay between fundamental understanding and technological innovation.

1.1.2 Importance of Sputtering in Thin-film Deposition, Surface Modification, and Nanotechnology

Sputtering plays a pivotal role in contemporary materials science and technology. Thin films produced by sputtering are essential in microelectronics, optoelectronics, energy conversion devices, and protective coatings. Some of the most prominent areas where sputtering has had transformative impact include:

1.1.2.1 Thin-film Deposition

Sputtering is a primary technique for depositing thin films with high uniformity, excellent adhesion, and controlled composition. Applications include metallization layers in integrated circuits, transparent conducting oxides for displays, and barrier coatings for packaging. Unlike evaporation, sputtering can deposit refractory materials with high melting points such as tungsten or titanium nitride [8].

1.1.2.2 Surface Modification

Beyond film growth, sputtering modifies surfaces directly. Ion bombardment can clean substrates, alter surface roughness, or induce chemical and structural changes. Ion-beam sputtering is widely used for surface patterning, depth profiling in analytical techniques such as secondary ion mass spectrometry (SIMS), and tailoring of catalytic activity [9].

1.1.2.3 Nanotechnology

In nanoscience, sputtering provides a pathway to engineer nanoscale materials and devices. Magnetron sputtering enables deposition of nanostructured thin films,

nanocomposites, and multilayer heterostructures with tailored magnetic, optical, or electronic properties [10]. Furthermore, sputtering-driven self-assembly of nanostructures on surfaces has emerged as a powerful method for producing nanopatterned templates.

1.1.2.4 Energy and Emerging Applications

In the energy sector, sputtered thin films are crucial for solar cells, fuel cells, and solid-state batteries [11]. Emerging applications include spintronic devices, quantum computing components, and advanced biomedical coatings where precise control of film composition and morphology is critical. Overall, the versatility and scalability of sputtering make it indispensable for both research and industrial production.

1.1.3 Scope

As the opening chapter of this book, the aim here is to establish a mechanistic foundation for sputtering that will guide the understanding of subsequent chapters focused on specific processes, materials, and applications. This chapter begins with the fundamental definition and historical perspective of sputtering, setting the stage for more detailed discussion of physical models, experimental techniques, and technological developments.

The mechanistic understanding will be developed by:

- Reviewing the physics of ion–solid interactions and collision cascades.
- Explaining the theoretical models, from Sigmund’s seminal work to modern computational approaches.
- Analyzing how experimental observations support or challenge existing models.
- Identifying parameters that govern sputtering efficiency and surface morphology.
- Linking fundamental processes to practical deposition methods such as magnetron sputtering, reactive sputtering, and HiPIMS.

By bridging theoretical insights with practical applications, this chapter not only highlights the importance of sputtering in modern science and technology but also prepares readers to appreciate the deeper mechanistic details and advanced applications discussed in later chapters.

Sputtering is both an ancient phenomenon and a cutting-edge technology. From Grove’s [3] early observations of cathode erosion to modern-day plasma-assisted sputtering systems, its evolution reflects the close relationship between physics, materials science, and engineering innovation. As we advance into an era of nanotechnology and quantum devices, sputtering continues to provide a powerful, flexible, and indispensable method for designing materials with atomic-scale precision. This chapter serves as the entry point for a comprehensive exploration of sputtering mechanisms. By focusing on the interplay between theory, experiment, and applications, it aims to give readers a holistic framework for understanding and applying sputtering in diverse scientific and technological contexts.

1.2 Fundamentals of Sputtering

Sputtering is inherently a nonequilibrium surface phenomenon governed by the interaction of energetic particles with solid targets. Figure 1.1 shows the basic phenomenon of sputtering. In this process, atoms are ejected from the surface of a solid target when it is bombarded by energetic particles. The sputtering process operates through the formation of a glow discharge between two electrodes placed within a sealed vacuum chamber. To initiate this discharge, the chamber is first evacuated to a base pressure typically below 10^{-4} Pa, after which an inert sputtering gas (most commonly argon) is introduced. When a sufficiently high direct current (DC) voltage is applied across the electrodes, the gas becomes partially ionized, leading to the establishment of an electrical discharge. The positively charged ions are then accelerated toward the target, which serves as the cathode, causing the ejection of atoms from their surface along with the release of secondary electrons. As this interaction continues, the system quickly stabilizes into a self-sustaining steady-state discharge.

The technique typically takes place in a vacuum chamber, where a glow discharge is established between two electrodes to generate the energetic species responsible for the ejection. While the general concept involves ion bombardment ejecting atoms, the underlying physics is complex and depends on atomic-scale processes such as ion–solid interactions, energy transfer, cascade formation, and atom emission dynamics. A mechanistic understanding requires an exploration of these fundamentals, which are elaborated in this section.




Figure 1.1 Basic phenomenon of sputtering. *Source:* Adapted from Ghazal H and Sohail N (2023).




Figure 1.2 Ion–solid interaction schematic. *Source:* Zhao et al., (2019) / MDPI / CC BY 4.0.

1.2.1 Ion–Solid Interactions

When energetic ions bombard a solid surface, they interact with the atoms in the target primarily through two fundamental mechanisms: **nuclear collisions** and **electronic interactions**. Figure 1.2 represents the ion–solid interaction schematic. In nuclear or elastic collisions, the incident ion directly transfers its momentum to the nuclei of the target atoms. This type of interaction dominates in the low-to-intermediate energy range, typically from around 10 eV up to 100 keV, which corresponds to the energy regime most relevant to sputtering [1, 9]. During these collisions, the incoming ion can displace atoms from their lattice sites, generating collision cascades that may eject atoms from the surface. In contrast, electronic or inelastic interactions become increasingly important at higher ion energies, generally above 100 keV. In this regime, the ion loses energy primarily to the electronic subsystem of the material rather than to the atomic nuclei. Transferred energy can lead to ionization, electronic excitations, and localized heating, a process commonly referred to as electronic stopping [12]. While electronic interactions do not typically result in direct sputtering through atomic displacement, they can influence the thermal and structural state of the target material, thereby affecting sputtering efficiency and surface modification. Together, these nuclear and electronic processes determine how energy is deposited in the solid and govern the resulting physical outcomes during ion–solid interactions.

The stopping power (S), representing energy loss per unit distance, is central to describing these processes. It is expressed as:

$$S = \left(\frac{dE}{dx} \right) = S_n + S_e \quad (1.1)$$

where S_n is the nuclear stopping power, and S_e is the electronic stopping power. For sputtering-relevant energies (hundreds of electronvolts to a few kiloelectronvolts), S_n dominates, enabling efficient momentum transfer that ejects atoms from the surface [2]. Furthermore, the penetration depth of ions depends on their energy and mass, as well as the target material. For example, light ions such as Ar^+ penetrate deeper than heavy ions at the same energy, influencing both sputtering yield and the depth profile of damage.

1.2.2 Threshold Energy and Sputtering Yield

1.2.2.1 Threshold Energy

For sputtering to occur, the ion must transfer sufficient energy to overcome the surface binding energy (U_0) of target atoms. The minimum incident ion energy required is referred to as the threshold energy (E_t). It depends on:

- Atomic binding energy of the target material
- Mass ratio of projectile to target atom
- Ion incidence angle

Typical values of E_t range between 20 and 100 eV for most metals and oxides [4]. For lighter ions (e.g., He^+), higher incident energies are needed due to inefficient momentum transfer.

1.2.2.2 Sputtering Yield

The sputtering yield (Y) quantifies the efficiency of sputtering and is defined as:

$$Y = \frac{N_{\text{ejected}}}{N_{\text{incident}}} \quad (1.2)$$

where N_{ejected} is the number of atoms ejected, and N_{incident} is the number of incident ions.

Sigmund's theory [1] provided the first quantitative model, relating sputtering yield to nuclear stopping power and surface binding energy:

$$Y(E) \propto \frac{S_n(E)}{U_0} \quad (1.3)$$

This implies that the yield increases with higher nuclear stopping but decreases with larger binding energy. Experimental studies confirm that sputtering yield generally increases with ion energy up to a certain value (a few kiloelectronvolts), beyond which it saturates or decreases due to deeper ion penetration [2]. Additionally, angle of incidence plays a critical role. At oblique angles (60° – 80°), yields can be several times higher than at normal incidence due to shallower penetration and increased near-surface collisions [13].

1.2.3 Momentum Transfer and Collision Cascades

The core of sputtering lies in momentum transfer between the incident ion and target atoms. This interaction initiates a collision cascade, a sequence of successive collisions that redistribute energy and momentum in the near-surface region. In the binary collision approximation (BCA), the interaction is modeled as a series of two-body elastic collisions. This is valid in the keV range and provides the basis for Monte Carlo simulations (e.g., transport of ions in matter [TRIM], SRIM codes) [12]. During the cascade, some atoms may gain sufficient energy to overcome U_0 and escape the surface, while others remain displaced within the lattice, creating defects. The efficiency of cascades depends on the mass ratio of projectile to target. If the projectile is lighter, it transfers momentum inefficiently, resulting in deep implantation rather than surface ejection. However, if the projectile mass is comparable to or heavier than the target atom, efficient near-surface cascades are generated, leading to higher sputtering yields [2]. Cascade theory also explains why preferential sputtering occurs in alloys and compounds—lighter or more weakly bound atoms are preferentially ejected, altering surface composition [9].

1.2.4 Primary vs. Secondary Sputtering Phenomena

Sputtering is not limited to primary ion–target interactions. Several secondary phenomena contribute significantly to the overall process:

1. Primary Sputtering

- Atoms are directly ejected by collision cascades initiated by primary ion impacts.
- Dominant mechanism in conventional sputtering systems.

2. Secondary Sputtering Processes

- **Ion-induced Desorption:** Secondary particles (adsorbed gases or contaminants) are released from the surface under bombardment.
- **Electronic Sputtering:** At very high ion energies, electronic excitations can result in bond breaking and atom ejection, especially in insulators.
- **Knock-on Sputtering:** Ejected atoms may reimpact the surface and cause further sputtering, enhancing overall yield.
- **Chemical Sputtering:** In reactive environments (e.g., O_2 , N_2 plasmas), chemical reactions between incoming ions and surface atoms can form volatile species that desorb more easily [6].

These secondary processes become particularly important in reactive sputtering and ion beam sputtering, where chemical and electronic contributions complement physical sputtering.

1.2.5 Energy and Angular Distribution of Ejected Atoms

The nature of ejected atoms is not uniform; instead, their energy and angular distributions follow specific patterns that provide insight into the underlying mechanisms.

- **Energy Distribution**

Thompson (1968) described the kinetic energy distribution of sputtered atoms as [14]:

$$f(E) \propto \frac{E}{(E + U_0)^3} \quad (1.4)$$

where U_0 is the surface binding energy of the target atoms. This distribution implies the most sputtered atoms have low energies (1–10 eV). A small fraction has higher energies (>20 eV), enabling surface diffusion or implantation in nearby substrates. These energy levels are much higher than thermal evaporation energies (~0.1 eV), giving sputtered films unique properties such as dense microstructures and good adhesion.

- **Angular Distribution**

Angular emission generally follows a cosine law relative to the normal surface:

$$I(\theta) \propto \cos^n(\theta) \quad (1.5)$$

where “ n ” varies depending on ion energy and material. At low ion energy, emission is close to cosine ($n \approx 1$). At higher energies or oblique incidence, distributions become more forward-peaked due to directional momentum transfer [14]. Angular effects are technologically important: they influence film uniformity in sputtering systems and are exploited in ion beam shaping for nanofabrication.

1.3 Types of Sputtering

Sputtering as a physical vapor deposition (PVD) technique has evolved through several configurations, each designed to overcome specific challenges such as plasma stability, deposition rate, target material restrictions, and film uniformity. Among the most common sputtering techniques are DC sputtering, RF sputtering, and magnetron sputtering. Each type of sputtering has its own operational principles, benefits, and limitations, which influence its applicability in microelectronics, optics, and thin-film device fabrication. Understanding the physics and engineering aspects of these sputtering types is essential to select the right technique for particular applications.

1.3.1 DC Sputtering

DC sputtering is one of the earliest and simplest forms of sputtering, widely employed in research and industrial applications. In DC sputtering, a constant voltage is applied between the target (cathode) and the substrate (anode), which establishes a glow discharge in a low-pressure inert gas atmosphere, usually argon. Positive argon ions are accelerated toward the negatively biased target, where they transfer momentum and eject surface atoms through collision cascades. These

atoms then condense on the substrate to form a thin film [5, 15]. DC sputtering is efficient when working with electrically conductive targets such as metals and conductive oxides. The continuous supply of electrons from the target helps sustain the discharge, making the plasma stable under steady-state conditions. One of the advantages of DC sputtering is its simplicity, relatively low cost, and ease of control, which makes it suitable for large-area coatings and industrial-scale processes [16]. The sputtering rate can be easily tuned by adjusting the DC power, working gas pressure, and target–substrate geometry. However, DC sputtering faces significant limitations when applied to insulating targets such as ceramics and dielectric materials. During sputtering of insulators, charge accumulation occurs on the target surface because electrons cannot freely flow to neutralize the positive ions bombarding it. This results in a phenomenon known as “arcing,” which disrupts plasma stability, damages the growing film, and reduces deposition efficiency [6]. To overcome this limitation, alternative sputtering methods such as RF sputtering were developed. Despite its limitations with insulating materials, DC sputtering remains a widely used deposition technique in the microelectronics and decorative coating industries, where conductive targets are required. Applications include deposition of aluminum, copper, titanium, and other metallic thin films for integrated circuits, hard coatings, and optical reflective layers. The method also serves as the baseline upon which more advanced sputtering techniques have been built.

1.3.2 RF Sputtering

To overcome the drawbacks of DC sputtering, especially for insulating targets, RF sputtering was developed. RF sputtering is usually operated at 13.56 MHz. The electrode polarity is alternately switched by an alternating high-frequency power source that is linked to the target in RF sputtering. Even for dielectric materials, this alternating polarity stabilizes the discharge by preventing charge accumulation on the target surface by periodically attracting electrons to neutralize the accumulated positive charge [16, 17]. Physics of RF sputtering involves both capacitive and inductive coupling of the plasma. At high frequencies, electrons, being more mobile than ions, can respond quickly to the oscillating electric field, while the heavier ions remain relatively unaffected within a single RF cycle. This imbalance results in the formation of a negative self-bias at the target, ensuring continuous ion bombardment of the target surface [5]. This mechanism makes RF sputtering highly versatile, enabling deposition of insulating oxides, nitrides, carbides, and ceramic films. One important aspect of RF sputtering is the so-called “RF sheath” formed at the target surface. The self-bias potential across this sheath accelerates ions toward the target, creating the sputtering process. Meanwhile, secondary electrons generated during ion bombardment contribute to plasma maintenance, improving sputtering efficiency. The versatility of RF sputtering allows deposition of high-quality films with good adhesion, stoichiometric transfer, and uniform thickness, making it an indispensable tool in thin-film technology [6]. RF sputtering, however, is more complex and expensive compared to DC sputtering due to the need for impedance matching networks and specialized RF power supplies. Moreover, the deposition

rate in RF sputtering is typically lower than in DC sputtering, particularly for conductive targets, because of the alternating nature of the applied power. Nevertheless, its ability to deposit films from insulating targets has made RF sputtering essential in the fabrication of optical coatings, dielectric layers for microelectronics, and advanced ceramic films. For example, SiO_2 , Al_2O_3 , and TiO_2 thin films are often deposited using RF sputtering for applications in integrated circuits, photonics, and sensors [8].

1.3.3 Magnetron Sputtering

Magnetron sputtering represents a major advancement in sputtering technology, introduced to enhance deposition rates and plasma confinement. In magnetron sputtering, magnetic fields are used to trap secondary electrons close to the target surface, thereby increasing the ionization probability of the sputtering gas. The combination of electric and magnetic fields produces an $\mathbf{E} \times \mathbf{B}$ drift, forcing electrons into helical trajectories near the target. This localized electron confinement results in higher plasma densities near the target surface, increasing ion bombardment and, consequently, the sputtering yield [5, 6]. The enhanced plasma confinement in magnetron sputtering reduces the working gas pressure required for stable operation, thereby increasing the mean free path of sputtered atoms and improving film quality. Compared to conventional DC or RF sputtering, magnetron sputtering achieves deposition rates up to an order of magnitude higher, making it highly efficient for large-scale and high-throughput applications [16]. Magnetron sputtering can be operated in either DC or RF modes, depending on the target material. DC magnetron sputtering is widely used for conductive materials, while RF magnetron sputtering is suitable for insulating targets. Another variant, mid-frequency magnetron sputtering (20–200 kHz), is employed for reactive sputtering of dielectric films, reducing arcing issues associated with pure DC sputtering [18]. A significant improvement in magnetron sputtering is the introduction of unbalanced magnetrons, where the magnetic field lines are designed to extend beyond the target region, allowing more ion flux to reach the substrate. This modification enhances film density, adhesion, and microstructural control [6].

Furthermore, modern HiPIMS represents a state-of-the-art development that employs short, high-power pulses to achieve high ionization of sputtered species, enabling dense and high-quality films with superior adhesion and smooth morphology [19]. HiPIMS represents a significant advance over conventional sputtering techniques, providing dense plasmas with high ionization fractions. In HiPIMS, very high peak power densities (on the order of kW/cm^2) are applied in short pulses, typically tens to hundreds of microseconds, with low duty cycles to avoid target overheating. The short, intense power pulses in HiPIMS generate a highly ionized sputtered flux, with ionization fractions exceeding 50% for many metals, compared to less than 10% in conventional DC sputtering. This ionization enhances control over film growth, enabling denser, smoother, and more adherent coatings. The energetic ion bombardment also promotes better step coverage in high-aspect-ratio structures, making HiPIMS highly attractive for semiconductor

and microelectronics applications. HiPIMS plasmas are characterized by high electron densities ($>10^{19}/\text{m}^3$) and increased ion energies, resulting in improved film densification and adhesion. Although HiPIMS deposition rates are typically lower than those of DC sputtering due to reduced time-averaged power, recent innovations such as modulated pulsed power supplies and hybrid processes are addressing this limitation. Applications of magnetron sputtering are extensive, including deposition of metals, oxides, nitrides, and multilayer coatings for microelectronics, hard coatings, optical filters, and decorative finishes. For example, TiN and DLC (diamond-like carbon) coatings deposited by magnetron sputtering are widely used in cutting tools, while multilayer interference coatings for optics often rely on this technique [8].

Beyond DC, RF, and magnetron sputtering, several specialized sputtering techniques have been developed to further improve control, deposition rate, and film quality. Reactive sputtering introduces reactive gases (e.g., oxygen, nitrogen) into the plasma to form compound films such as oxides and nitrides. Pulsed DC sputtering is employed to mitigate arcing during reactive sputtering of insulating films, offering better plasma stability than continuous DC sputtering. HiPIMS, as mentioned earlier, has gained significant attention for producing highly ionized fluxes of sputtered atoms, enabling dense microstructures and superior film properties. Dual magnetron sputtering systems, where two magnetron targets are driven in mid-frequency alternating polarity, are also used for reactive sputtering to balance charge accumulation [19]. These modern innovations highlight the continuous evolution of sputtering technologies to meet the demands of advanced materials and nanotechnology applications. The different types of sputtering—DC, RF, and magnetron—represent critical milestones in the evolution of thin-film deposition technology. DC sputtering offers simplicity and efficiency for conductive targets, RF sputtering extends the capability to insulating materials, and magnetron sputtering significantly enhances deposition rates and film quality through plasma confinement. HiPIMS and dual magnetron sputtering continue to push the boundaries of performance, enabling high-quality thin films with precise control over composition and microstructure.

1.4 Theoretical Models of Sputtering

Understanding the theoretical basis of sputtering is essential for bridging experimental observations with predictive modeling of thin-film growth, surface modification, and nanoscale structuring. Over the decades, several models have been developed to describe the ejection of atoms under energetic ion bombardment, ranging from analytical frameworks to computationally intensive simulations. This section explores the most widely used theoretical approaches, beginning with Sigmund's classical model, and progressing toward modern atomistic and numerical methods such as Monte Carlo simulations, BCA, and molecular dynamics (MD). Their advantages, limitations, and ongoing challenges are highlighted to provide a balanced view of the current state of sputtering theory.

1.4.1 Sigmund's Theory of Sputtering

The pioneering theoretical framework for sputtering was developed by Peter Sigmund in the late 1960s and early 1970s. Sigmund's theory laid the foundation by treating sputtering as a momentum-transfer process arising from nuclear collisions between incident ions and target atoms. The model assumes that when an energetic ion penetrates a solid, it loses energy through successive binary collisions with the lattice atoms. A portion of this energy is transferred to surface atoms located within a so-called “collision cascade,” and if the transferred energy exceeds the surface binding energy, atoms are ejected from the surface [1]. Mathematically, Sigmund derived the sputtering yield Y —defined as the number of atoms ejected per incident ion—as a function of the stopping cross section and surface binding energy. The simplified expression is:

$$Y(E) \propto \frac{\alpha S_n(E)}{U_s} \quad (1.6)$$

where $S_n(E)$ is the nuclear stopping cross section, U_s is the surface binding energy, and α is a dimensionless constant depending on the ion/target mass ratio.

This theory provides a direct link between measurable sputtering yields and fundamental material properties such as surface binding energy, ion mass, and incident ion energy. One of its strengths lies in its ability to qualitatively explain why sputtering yields increase with ion energy up to a certain point, and why heavier ions tend to produce higher yields compared to lighter ions at similar energies [9]. However, the model has notable limitations. It is valid primarily for amorphous or polycrystalline materials, where atomic positions can be treated statistically. In crystalline solids, channeling effects—where ions penetrate deeper along low-index crystallographic directions—can lead to deviations from predicted yields. Furthermore, Sigmund's theory neglects electronic stopping and thermal spike effects, which are important at higher ion energies or when dealing with metals and semiconductors. Despite these limitations, the framework remains the cornerstone of sputtering theory and continues to influence subsequent models [2, 20].

1.4.2 Monte Carlo Simulations and TRIM

As computational resources advanced, statistical simulation approaches based on the Monte Carlo method became increasingly popular for studying sputtering. Monte Carlo simulations treat the trajectory of ions as a series of stochastic events governed by probabilistic scattering laws. By simulating a large number of ion trajectories and interactions, average quantities such as sputtering yield, depth distribution of implanted ions, and energy deposition profiles can be obtained. One of the most influential codes is TRIM, developed by [21]. TRIM uses BCAs within a Monte Carlo framework to simulate ion–solid interactions. The program can calculate implantation depth profiles, sputtering yields, and damage distributions for a wide range of ion–target combinations. Its versatility has made TRIM the standard tool in both academic research and industrial applications, particularly in

Table 1.1 Comparison between TRIM-predicted and experimentally measured sputtering yields for selected ion–target systems.

Ion–target system	Ion energy (keV)	Incidence angle (°)	TRIM-predicted yield (atoms/ion)	Experimental yield (atoms/ion)	References
Ar ⁺ → Cu	1	0	2.1	2.5 ± 0.3	[1]
Ar ⁺ → Si	1	0	0.8	1.0 ± 0.2	[9]
Kr ⁺ → Si	1	0	1.5	1.7 ± 0.2	[14, 20]
Ar ⁺ → Al	1	0	1.1	1.2 ± 0.1	[4]
Xe ⁺ → Au	1	0	7.4	7.8 ± 0.4	[2]

semiconductor processing. For instance, TRIM simulations have been used to predict dopant profiles in silicon, to optimize sputter-etching parameters in microelectronics fabrication, and to study surface modification in ceramics and polymers [12]. By comparing TRIM outputs with experimental measurements, researchers can fine-tune sputtering parameters to achieve desired thin-film properties (Table 1.1).

The strength of TRIM lies in its efficiency and broad applicability. Yet, it has limitations—particularly in handling dynamic surface changes. Since TRIM assumes a static target, it cannot easily account for surface roughening, redeposition, or compound formation during sputtering. In recent years, dynamic versions such as SDTrimSP (a dynamic TRIM code with sputtering and redeposition) have been developed to address these issues [22]. Nevertheless, TRIM remains one of the most widely cited and practically useful models in the sputtering community.

1.4.3 BCA

The BCA underpins both Sigmund’s theory and Monte Carlo methods such as TRIM. In the BCA framework, the complex many-body problem of ion–solid interaction is reduced to a series of independent two-body collisions between the incident ion and individual target atoms. Each collision is treated using classical mechanics, with scattering angles determined by interatomic potentials [23]. The advantage of BCA lies in its relative simplicity. By assuming that collisions are independent, one can calculate trajectories, energy transfers, and displacement cascades with manageable computational resources. This makes BCA particularly attractive for high-energy ion bombardment where collisions are well separated in time and space. However, the approximation breaks down when collective effects become significant, such as in dense collision cascades or when low-energy ions cause overlapping displacement events. BCA also neglects electronic excitations and thermalization effects that may influence sputtering yields and defect generation. Despite its limitations, BCA continues to provide the theoretical foundation for many practical simulation codes. When combined with experimental calibration, BCA models yield sufficiently accurate results for many engineering applications, from ion implantation to plasma etching.

1.4.4 Molecular Dynamics Approaches

While BCA and Monte Carlo methods rely on simplifying assumptions, **MD simulations** provide a more atomistic approach by solving Newton's equations of motion for a system of atoms under interatomic forces. In sputtering studies, MD allows direct observation of how incident ions interact with a target surface, leading to collision cascades, defect formation, and atom ejection. MD simulations use interatomic potentials such as Lennard–Jones, embedded atom method (EAM), or Tersoff potentials, depending on the material system under study. By explicitly tracking atomic trajectories, MD provides detailed insights into sputtering mechanisms that are difficult to capture with analytical models. For example, MD has revealed the importance of collective atomic motion, local heating (thermal spikes), and surface morphology evolution during sputtering of metals and ceramics [24]. The strength of MD lies in its ability to capture complex processes such as redeposition, defect clustering, and amorphization, which are often neglected in simpler models. However, the method is computationally expensive. Typical MD simulations are limited to systems of a few million atoms and time scales of nanoseconds, restricting their applicability to relatively small spatial and temporal domains. Hybrid approaches, where MD is combined with BCA or continuum models, are increasingly being explored to overcome these limitations [25].

1.4.5 Limitations of Existing Models and Ongoing Challenges

Despite decades of development, no single theoretical framework can fully describe sputtering across all energy regimes, material systems, and experimental conditions. Each model has inherent limitations:

- **Sigmund's theory** provides elegant analytical insights but oversimplifies by assuming amorphous targets and neglecting electronic effects.
- **Monte Carlo/ TRIM** methods are powerful for statistical predictions but struggle with dynamic surface evolution and compound formation.
- **BCA** captures binary interactions well but misses collective effects and thermal phenomena.
- **MD simulations** offer atomic-level accuracy but are constrained by computational limits.

One of the central challenges remains the incorporation of **electronic stopping mechanisms**. While nuclear stopping dominates at lower energies, electronic excitations can play a major role in high-energy sputtering, especially for insulators and semiconductors (Sigmund & Gras-Marti, 1981) [26]. Similarly, surface chemistry effects, such as oxidation or compound layer formation during sputtering in reactive environments, are often beyond the reach of current models. Ongoing research is focused on multiscale modeling approaches that integrate the strengths of different methods. For instance, BCA or Monte Carlo methods can provide initial conditions for MD simulations, while continuum models describe long-term surface evolution. The development of machine learning-assisted interatomic potentials also holds promise for extending the accuracy and efficiency of MD simulations,

enabling larger and longer simulations of sputtering processes [27]. Despite significant progress, challenges remain in unifying these frameworks and extending their applicability to dynamic, chemically complex, and multiscale environments. Addressing these limitations will be essential for advancing sputtering as a precise and predictive tool in thin-film deposition and nanotechnology.

1.5 Mechanistic Pathways in Sputtering

Sputtering is fundamentally governed by the interactions between incident energetic ions and the solid target surface. The mechanistic pathways underlying this phenomenon are complex, involving multiple physical processes that occur on ultrafast timescales and within nanometer-scale collision cascades. These mechanisms dictate not only the sputtering yield but also the energy distribution of ejected atoms, the resulting film microstructure, and the evolution of surface morphology. This section delves into the physical pathways of sputtering, emphasizing the interplay between elastic and inelastic collisions, energy regimes, ion species, surface binding energies, preferential sputtering, and defect formation.

1.5.1 Elastic vs. Inelastic Collision Processes

When an energetic ion approaches the target surface, its interaction with target atoms can be broadly classified into elastic and inelastic collisions. Elastic collisions involve momentum transfer between the ion and the nuclei of the target atoms, while inelastic collisions correspond to energy dissipation via electronic excitations or ionization. In elastic collisions, the projectile ion undergoes a deflection after striking a target atom, conserving total kinetic energy but redistributing momentum within the lattice. These collisions are responsible for initiating collision cascades, where recoiling target atoms displace others, leading to ejection of atoms at or near the surface [1]. In contrast, inelastic collisions transfer part of the ion's energy to the electronic subsystem of the material, exciting valence electrons or producing electron-hole pairs [28]. Although electronic energy loss is often dominant at high ion energies (>100 keV), nuclear stopping (elastic scattering) remains the principal sputtering mechanism in the typical sputtering regime of 100 eV to a few kiloelectronvolts [2]. Figure 1.3 represents the schematic diagram illustrating the elastic and inelastic collisions during ion-target interaction.

A key theoretical model that unifies these interactions is Sigmund's theory of sputtering, which treats sputtering because of energy deposition by an incident ion in the near-surface region [1]. The spatial distribution of this deposited energy, coupled with the surface binding energy, determines the sputtering yield. Importantly, the relative contributions of elastic and inelastic collisions vary with ion energy, mass, and target composition. For example, heavy ions such as Xe^+ favor nuclear stopping and thus higher sputtering yields, while lighter ions like He^+ predominantly lose energy via electronic processes, often producing minimal sputtering.




Figure 1.3 Schematic diagram illustrating the elastic and inelastic collisions during ion–target interaction. World of Cats & Dogs. <https://ena.our-dogs.info/facts-sh.html>.

1.5.2 Sputtering Under Low-energy vs. High-energy Ion Bombardment

The incident ion energy plays a decisive role in controlling sputtering efficiency and mechanism. At low energies (10–200 eV), the ion may not penetrate deeply into the target, and sputtering occurs mainly via surface collision events. In this regime, the sputtering yield is low because much of the projectile’s energy is dissipated elastically in near-surface atoms, without sufficient recoil to overcome surface binding energies. This is sometimes referred to as the threshold regime, where sputtering can occur only if the ion energy exceeds the material’s effective surface binding energy [9]. In the intermediate energy regime (200 eV–10 keV), sputtering is most efficient. The ion penetrates a few nanometers to tens of nanometers into the target, initiating collision cascades that transfer energy to multiple atoms. The cascades result in the ejection of atoms when recoils reach the surface with sufficient energy to overcome binding forces. Most practical sputtering applications, such as magnetron sputtering, operate in this regime. At high energies (>100 keV), ions penetrate deeply into the bulk material, depositing much of their energy far below the surface. Although electronic stopping becomes significant, the fraction of energy available for near-surface displacement decreases, reducing sputtering efficiency. However, such energies are of interest in ion implantation and radiation damage studies rather than thin-film deposition [28].

1.5.3 Role of Ion Species (Ar^+ , Kr^+ , Xe^+ , Etc.)

The choice of ion species in sputtering processes significantly affects the sputtering yield and film properties. Noble gas ions such as Ar^+ , Kr^+ , and Xe^+ are most

commonly employed because of their chemical inertness, which avoids unwanted chemical reactions with the target or deposited film. The mass of the ions directly influences the momentum transfer during collisions. Lighter ions (e.g., He^+ , Ne^+) impart less momentum, leading to lower sputtering yields but potentially smoother film morphologies due to reduced damage. Heavier ions such as Xe^+ deposit energy more efficiently into the lattice, producing higher sputtering yields but also increasing the probability of subsurface damage and defect formation [2]. Among these, Ar^+ has become the standard choice in magnetron sputtering due to its balance of sputtering efficiency, availability, and cost-effectiveness. Kr^+ and Xe^+ , while less common, are employed in applications requiring higher yields or specialized surface modifications.

1.5.4 Surface Binding Energy Considerations

The sputtering process is critically dependent on the surface binding energy (U_s) of the target atoms, which represents the minimum energy required to eject an atom from the lattice. Materials with lower binding energies, such as metals, generally sputter more easily than ceramics or covalently bonded semiconductors. For example, the surface binding energy of copper (~ 3.5 eV) is considerably lower than that of SiO_2 (~ 8.0 eV), making copper easier to sputter under identical ion conditions [2]. Additionally, temperature effects can alter binding energies and, consequently, sputtering yields. At elevated temperatures, thermal vibrations weaken atomic bonds, lowering effective binding energies and enhancing sputtering.

1.5.5 Preferential Sputtering in Multicomponent Materials

In multicomponent targets such as alloys, ceramics, or compound semiconductors, sputtering does not always proceed uniformly across constituent elements. Instead, one species may sputter more readily than another, a phenomenon known as preferential sputtering. This occurs when the components have significantly different atomic masses, binding energies, or chemical affinities. For example, in GaAs' sputtering under Ar^+ bombardment, Ga tends to sputter more efficiently than As due to its lower binding energy. As a result, the surface composition becomes enriched in the less easily sputtered species [29]. Preferential sputtering has important implications for film stoichiometry and surface chemistry. In thin-film deposition, it may lead to compositional deviations between the target and the deposited layer. Similarly, in surface analysis techniques such as SIMS, preferential sputtering can complicate depth profiling by distorting apparent elemental distributions [30].

1.5.6 Sputtering-induced Defect Formation and Surface Morphology Changes

Beyond atom ejection, sputtering modifies the structural and morphological characteristics of the target surface. Ion bombardment introduces point defects, dislocations, and vacancy clusters, particularly under high fluence conditions [28]. The defect




Figure 1.4 A: AFM images of pristine and 100 keV Ar⁺ ion-irradiated Si samples (a) Pristine and irradiated samples with (b) 3×10^{17} , (c) 5×10^{17} , (d) 7×10^{17} , and (e) 9×10^{17} ions/cm² (all images are in 5 μm × 5 μm scan size) with corresponding wavelength distribution shown in B. *Source:* [32] / Beilstein Journal of Nanotechnology / CC BY 4.0.




Figure 1.5 A: AFM images of pristine and 100 keV Ar⁺ ion-irradiated Ge samples (a) pristine, (b) 3×10^{17} , (c) 5×10^{17} , (d) 7×10^{17} , and (e) 9×10^{17} ions/cm² irradiated samples (all images are in 5 μm × 5 μm scan size), B: shows the corresponding wavelength distribution. *Source:* [32] / Beilstein Journal of Nanotechnology / CC BY 4.0.

density is strongly dependent on ion energy, mass, and target crystallinity. Sputtering can also produce significant surface roughening. At low energies, smooth erosion occurs, while at intermediate energies, collision cascades may generate ripple structures, cones, or even nanopatterns due to instability-driven surface evolution [31]. Such ion-induced self-organization has been exploited in nanofabrication to create ordered surface patterns. Additionally, prolonged bombardment can lead to amorphization of crystalline surfaces, particularly in covalently bonded materials like Si or GaN. These structural changes directly impact subsequent film growth, adhesion, and functional properties. For this, Figures 1.4 and 1.5 show the atomic force microscopy (AFM) images of pristine and 100 keV Ar⁺ ion-irradiated Si and Ge samples for their pristine and irradiated samples with (b) 3×10^{17} , (c) 5×10^{17} , (d) 7×10^{17} , and (e) 9×10^{17} ions/cm² with corresponding wavelength distribution, respectively. Table 1.2

Table 1.2 Summary of typical sputtering-induced defects and surface morphologies across different materials (metals, semiconductors, and ceramics).

Material type	Typical defects induced by sputtering	Characteristic surface morphologies	Remarks/physical origin
Metals (e.g., Cu, Al, Ni, and Ti)	• Vacancy clusters • Surface roughening • Redeposition of sputtered atoms • Dislocation loops and stacking faults	• Ripple-like or wavy surfaces • Grain boundary grooving • Hillock and cone formation	High atomic mobility leads to dynamic surface relaxation; defect annealing possible at elevated substrate temperatures
Semiconductors (e.g., Si, Ge, GaAs)	• Point defects (vacancies, interstitials) • Dangling bonds and surface amorphization • Interface mixing or contamination • Ion implantation damage	• Amorphous or roughened layers • Nanoscale pits or craters • Faceting along crystal orientations	Ion bombardment disrupts covalent bonding; defect generation affects electronic and optical properties
Ceramics/Oxides (e.g., Al_2O_3 , TiO_2 , ZrO_2 , SiO_2)	• Oxygen vacancies • Nonstoichiometry (cation/anion loss) • Microcracks and voids • Subsurface densification or sputter redeposition	• Columnar or porous morphology • Nodule or cone-like growth • Rough or granular texture	Low atomic mobility and high sputtering yield of lighter elements (e.g., O) cause nonstoichiometry and defect clustering
Nitrides/Carbides (e.g., TiN, SiC)	• Vacancies and interstitials (especially N or C loss) • Substoichiometric regions • Dislocation networks	• Dense columnar grains • Faceted or textured surface • Occasionally smooth amorphous surface (at low temperature)	Ion energy and substrate bias strongly influence film densification and microstructure evolution

summarizes the typical sputtering-induced defects and surface morphologies across different materials (metals, semiconductors, and ceramics).

1.6 Mechanistic Parameters Influencing Sputtering

Sputtering is a complex physical process governed by a wide range of mechanistic parameters that collectively determine the efficiency, quality, and reproducibility of thin-film growth. Unlike simple thermal evaporation, where material removal is dominated by vapor pressure and temperature, sputtering involves the interaction

of energetic ions with a condensed solid, triggering momentum transfer, collision cascades, and eventual ejection of atoms or clusters. Because of this ion–solid interaction nature, the dynamics of sputtering are highly sensitive to both material-intrinsic properties of the target and extrinsic operating conditions such as ion energy, incidence geometry, substrate environment, and plasma confinement. This section provides a detailed discussion of these factors, integrating theoretical models and experimental findings to explain how sputtering yields and film properties are influenced under various regimes.

1.6.1 Target Properties

The intrinsic properties of the target play a central role in determining sputtering behavior. Among the most critical are the atomic mass of the constituent elements, the degree of crystallinity, and the surface binding energy. The atomic mass directly influences the momentum transfer during ion bombardment. According to Sigmund’s theory of sputtering [1], the energy transferred in an elastic collision between an incident ion of mass M_1 and a target atom of mass M_2 is maximized when the mass ratio approaches unity. Thus, targets with atomic masses closer to that of the incident ion exhibit higher energy transfer efficiency, and consequently, higher sputtering yields. For example, Ar^+ ions sputter materials such as Ti, Ni, or Cu more efficiently compared to very light elements (C, B) or very heavy elements (W, Au) because of suboptimal momentum transfer. The binding energy (E_b) of surface atoms is another decisive parameter. Higher binding energy implies stronger cohesive forces within the lattice, which raises the energy threshold for sputtering. Materials such as graphite or oxides typically exhibit lower sputtering yields under identical bombardment conditions compared to metals like Ag or Cu due to differences in binding energy [2]. This dependency can be visualized in the comparative Table 1.3.

Crystallinity and surface orientation also exert measurable effects. Experimental observations reveal anisotropy in sputtering yields across crystallographic planes. For example, in single-crystal Si, the $\{111\}$ orientation exhibits lower yields than the $\{100\}$ orientation due to differences in surface atom density and binding configuration [8]. Furthermore, polycrystalline targets, with grain boundaries and defects, often demonstrate higher effective sputtering rates than single crystals because defects serve as low-binding-energy ejection sites.

1.6.2 Ion Energy and Incidence Angle

Perhaps, the most studied mechanistic parameter is the energy of incident ions. The sputtering yield exhibits a nonlinear dependence on ion energy. At low energies (below the threshold, typically < 20 eV), no sputtering occurs because the ions lack sufficient energy to overcome the surface binding energy. As ion energy increases into the 100 eV–1 keV range, sputtering yields rise sharply, reaching a plateau around several keV depending on the material [9]. Beyond this regime, further increases in ion energy may lead to deeper ion implantation and reduced surface sputtering efficiency,

Table 1.3 Typical surface binding energies (E_s) and corresponding sputtering yields (Y) of selected materials under Ar^+ bombardment at 1 keV.

Material (target)	Surface binding energy, E_s (eV/atom)	Sputtering yield, Y (atoms/ion)	References
Cu (Copper)	3.5	2.3	[1, 4]
Al (Aluminum)	3.4	1.1	[9]
Ag (Silver)	2.9	3	[2]
Si (Silicon)	4.7	0.9	[4, 22]
Ti (Titanium)	4.9	0.7	[22]
Au (Gold)	3.8	6.5	[9]
Fe (Iron)	4.3	1.5	[1, 14]
Ni (Nickel)	4.4	1.3	[4]
SiO_2 (Silica)	6.4	0.5	[4, 22]
TiO_2 (Titanium dioxide)	7.5	0.3	[9, 21]

as much of the energy is dissipated below the surface. Another important factor is the angle of incidence. When ions impinge at normal incidence (0°), momentum transfer is directed primarily into the bulk, resulting in moderate sputtering yields. As the incidence angle increases (30° – 60°), sputtering yields often increase due to more effective near-surface energy deposition. However, at very grazing incidences ($>80^\circ$), yields decrease sharply because ions are reflected rather than absorbed. Experimental studies confirm a maximum sputtering yield at incidence angles between 60° and 70° for many metallic targets [2]. The dependence of sputtering yield on the incidence angle of the incoming ions can be described by the semiempirical Yamamura model [2]. This model accounts for the enhanced sputtering that occurs at oblique ion incidence due to increased energy deposition near the surface. The relationship is given by:

$$Y(\theta) = Y(0) (\cos\theta)^{-f} \quad (1.7)$$

where $Y(0)$ is the sputtering yield at normal incidence, θ is the angle of incidence (measured from the surface normal), and f is a dimensionless, material-, and energy-dependent parameter typically ranging between 1 and 2. At grazing incidence, sputtering yields generally increase due to the longer path length of ions near the surface, while at very large angles ($>70^\circ$), reflection and reduced penetration depth lead to a drop in yield.

1.6.3 Substrate Temperature

The substrate temperature, although not directly influencing the sputtering yield at the target, plays a significant role in determining film morphology and secondary sputtering effects. Elevated temperatures enhance surface diffusion of adatoms, thereby

improving film crystallinity and reducing roughness [16]. However, at excessively high substrate temperatures, resputtering of deposited atoms can occur, lowering the net deposition rate. Thermal effects also influence defect dynamics. At low substrate temperatures, sputtering-induced damage such as vacancies or interstitials may accumulate, while higher temperatures enable dynamic annealing. For compound targets, such as oxides or nitrides, substrate temperature determines the volatility of lighter species (e.g., O, N), often leading to preferential sputtering. A notable example is the deposition of TiN films: at low substrate temperatures, the films are typically amorphous and porous, while at moderate temperatures (300–500°C), dense columnar grains are observed due to thermally activated surface diffusion [6].

1.6.4 Chamber Pressure and Gas Composition

Chamber pressure and gas composition dictate the plasma environment, which in turn controls the ion energy distribution and mean free path. At low pressures (<1 mTorr), ions experience fewer collisions, resulting in high-energy bombardment at the target and substrate. This condition enhances sputtering efficiency but may reduce plasma density, leading to nonuniform deposition. Conversely, high pressures (>10 mTorr) produce frequent collisions, reducing ion energy at the target but increasing plasma uniformity. Optimal sputtering typically occurs at intermediate pressures (3–10 mTorr). The working gas composition also strongly influences outcomes. Argon is the most common choice due to its inertness, appropriate mass, and ionization efficiency. However, alternative gases can be used to tailor sputtering. For example, Kr or Xe ions (heavier than Ar) deliver higher sputtering yields due to more effective momentum transfer, while lighter ions such as He are less efficient. In reactive sputtering, O₂ or N₂ is introduced alongside Ar to form compound films like oxides or nitrides. Control over the partial pressure of reactive gases is critical; excessive O₂ leads to target poisoning (formation of insulating oxide layers on metallic targets), which reduces deposition rates and destabilizes plasma [33].

1.6.5 Magnetic Confinement Effects

The introduction of magnetic fields in magnetron sputtering represents a major advance in enhancing plasma density and sputtering efficiency. By confining secondary electrons near the target surface through crossed $E \times B$ fields, magnetrons sustain higher ionization rates at lower operating pressures [34]. The degree of magnetic confinement influences both the ionization efficiency and the erosion profile of the target. Stronger confinement increases the local plasma density, thereby enhancing sputtering rates. However, it also leads to the well-known “race-track” erosion pattern on targets, which reflects the localized confinement of ions. In advanced systems such as HiPIMS, magnetic confinement is critical to sustaining high-density plasmas with nearly 100% ionization of the sputtered flux [7]. This enables better film densification and adhesion, albeit at reduced deposition rates compared to DC magnetron sputtering. Figure 1.6 illustrates the electron trajectories in a magnetron showing confinement loops and race-track erosion zones.




Figure 1.6 Illustration of electron trajectories in a magnetron showing confinement loops and race-track erosion zones.

1.6.6 Time Evolution and Steady-state Considerations

Sputtering is not a static process but evolves dynamically over time as the target and plasma conditions change. Early stages of sputtering may involve surface cleaning and conditioning, where contaminants or oxides are preferentially removed. Once steady state is achieved, the sputtering yield stabilizes, but this equilibrium depends on several competing processes. One such phenomenon is preferential sputtering in multicomponent targets. For example, in a TiO_2 target, oxygen atoms (lighter, weaker binding) are preferentially sputtered compared to Ti, leading to surface enrichment of Ti over time. Eventually, a steady-state composition develops that differs from the bulk stoichiometry [35]. Another time-dependent effect is target poisoning during reactive sputtering. As mentioned earlier, reactive gases such as O_2 or N_2 form compound layers on the target, drastically altering its sputtering characteristics. The transition between metallic and poisoned modes is often hysteretic, making process control challenging. Time-resolved diagnostics such as optical emission spectroscopy or mass spectrometry are therefore employed to monitor and stabilize reactive sputtering processes. Finally, prolonged sputtering leads to target erosion and morphology evolution. Erosion grooves, redeposition, and microstructural modifications affect the angular distribution and energy of sputtered species, thereby influencing long-term deposition uniformity. Figure 1.7 represents the time-resolved schematic of sputtering yield evolution in a Ti target under O_2 reactive sputtering, showing metallic, transition, and poisoned regimes.

1.7 Experimental Observations and Characterization

The experimental characterization of sputtering processes forms the essential bridge between theoretical models and practical applications. While the physics of sputtering has been extensively modeled through collision cascade theory, MD, and Monte Carlo simulations, it is the systematic collection of experimental evidence that validates,




Figure 1.7 Time-resolved schematic of sputtering yield evolution in a Ti target under O_2 reactive sputtering, showing metallic, transition, and poisoned regimes.

corrects, or refines such models. Reliable measurements of sputtering yield, surface composition, topography, and plasma characteristics are indispensable for understanding the fundamental mechanisms of atom ejection as well as for optimizing thin-film deposition processes in microelectronics, optics, protective coatings, and energy devices. In this section, the discussion is organized around the measurement of sputtering yield, surface analytical techniques, plasma diagnostics, and the crucial correlation between theoretical predictions and experimental outcomes.

1.7.1 Measurement of Sputtering Yield

Sputtering yield, defined as the average number of atoms ejected per incident ion, is the most direct metric of sputtering efficiency. Its measurement requires precise control over both the ion beam characteristics and the quantification of the ejected or deposited species. Several approaches have been developed, each with their advantages and limitations. One of the earliest and most straightforward methods involves gravimetric analysis, where the mass loss of a sputtered target is measured before and after ion bombardment using a high-precision microbalance. This technique offers direct yield values but demands a long sputtering time to ensure measurable mass differences, especially when dealing with materials of low sputtering rates. For instance, metals like tungsten or molybdenum may require extended ion exposure before detectable mass loss occurs. Another widely used approach relies on profilometry. In this method, a sputtered crater is created by ion bombardment, and the depth and volume of the crater are subsequently measured using stylus profilometry or optical profilometry. When combined with the known ion fluence, this allows accurate calculation of sputtering yield. The method is particularly useful for localized yield measurements and has been applied extensively in calibrating sputter depth profiling techniques. A third powerful method is based on quartz crystal microbalance (QCM) monitoring, which detects the deposition rate of sputtered material onto a quartz crystal sensor. By measuring the frequency shift of the crystal resonance, the deposited mass can be deduced with nanogram sensitivity. This technique is highly valuable in thin-film deposition systems, where real-time monitoring of sputtering yield under plasma conditions is required. It allows

simultaneous correlation of yield with process parameters such as gas pressure, bias voltage, or target material.

Rutherford backscattering spectrometry (RBS) can also be employed indirectly, by analyzing the depletion of specific elements from the sputtered surface. Although less common, this approach provides element-specific information, which is particularly useful in multicomponent systems such as alloys, oxides, or ceramics. It should be emphasized that sputtering yield is strongly dependent on several parameters: incident ion energy, angle of incidence, ion species, and target binding energy. For instance, yields generally increase with energy up to a few kiloelectronvolts before saturating, and the angular dependence typically shows a maximum at oblique incidence around 60° . Systematic yield measurements thus serve not only as quantitative benchmarks but also as fingerprints of the underlying sputtering mechanisms.

1.7.2 Surface Analytical Techniques

Since sputtering intrinsically alters the surface of a material, the characterization of composition, morphology, and microstructure before and after ion bombardment is essential. A suite of advanced surface analytical tools provides complementary insights.

X-ray photoelectron spectroscopy (XPS) is one of the most powerful techniques for probing the chemical composition and electronic states of sputtered surfaces. By analyzing the binding energies of emitted photoelectrons, XPS can quantify elemental composition within the top few nanometers and reveal changes in oxidation states or chemical bonding induced by sputtering. For example, preferential sputtering often results in surface enrichment of lighter elements, which can be directly tracked by XPS. In addition, depth profiling combined with sputtering allows three-dimensional chemical mapping of multilayer structures.

Auger electron spectroscopy (AES) offers complementary capabilities with higher surface sensitivity, probing the outermost atomic layers. Because AES can be performed with fine electron beams, it also provides spatially resolved chemical mapping at the micron or even submicron scale. When coupled with sputter depth profiling, AES becomes a key technique for analyzing thin-film stacks in microelectronics.

Scanning electron microscopy (SEM) plays a central role in examining the morphology of sputtered surfaces and deposited films. Ion bombardment often leads to roughening, ripple formation, or nanostructuring depending on the sputtering conditions. SEM allows direct visualization of these features, offering both qualitative insights and quantitative data when combined with image analysis software. High-resolution SEM has been extensively used to monitor the growth of columnar structures in sputtered films.

AFM extends surface characterization to the nanometer scale, providing quantitative topographical maps with vertical resolution better than 1 nm. AFM measurements of surface roughness (root mean square values), ripple periodicity, or

nanoparticle formation after sputtering offer critical input for correlating surface evolution with ion energy and fluence. For example, AFM studies have shown that ripple wavelength scales with the square root of ion energy, consistent with predictions from the Bradley–Harper model.

By combining these techniques—XPS/AES for composition, SEM for microstructure, and AFM for nanoscale morphology—a comprehensive understanding of sputtering-induced surface changes can be established.

1.7.3 Plasma Diagnostics

While sputtering is fundamentally a surface process, the plasma environment that delivers energetic ions plays a decisive role. Therefore, plasma diagnostics are essential for correlating sputtering behavior with plasma characteristics such as ion energy distribution, electron density, and excitation states. The Langmuir probe is the most widely used diagnostic tool for measuring plasma parameters. By sweeping the probe bias and recording the current–voltage characteristics, one can extract electron temperature, plasma density, and floating potential. These parameters directly influence the energy with which ions are accelerated toward the target. For instance, higher plasma density typically translates into enhanced ion flux and higher sputtering rates. Optical emission spectroscopy (OES) provides a noninvasive method to probe plasma composition and excitation states. By monitoring characteristic emission lines, OES can identify the presence of sputtered species in plasma as well as the degree of ionization of the working gas. For example, in reactive sputtering of metal oxides or nitrides, OES allows real-time monitoring of oxygen or nitrogen emission lines, enabling control over the transition between metallic and compound sputtering regimes. Advanced techniques such as mass spectrometry (MS) and laser-induced fluorescence (LIF) have also been applied in research contexts to probe ion energy distributions and metastable populations in sputtering plasmas. These diagnostics deepen our understanding of energy transfer processes, especially in HiPIMS, where highly ionized sputtered fluxes are observed. Plasma diagnostics are therefore indispensable for process optimization. They not only confirm theoretical expectations about ion fluxes but also reveal complex, nonlinear behavior that arises in reactive plasmas, magnetron geometries, and pulsed power conditions.

1.7.4 Correlation Between Theory and Experiments

The final and most critical step in sputtering research is establishing meaningful correlations between theoretical predictions and experimental observations. Theoretical models—such as Sigmund’s linear collision cascade theory, Monte Carlo simulations using TRIM/SRIM codes, and MD simulations—provide predictions of sputtering yield, angular distributions, and energy spectra of ejected atoms. However, discrepancies often arise due to assumptions such as homogeneous targets, neglect of surface chemistry, or idealized ion distributions. Experimental yield

measurements frequently validate the overall trends predicted by theory, such as the dependence on ion energy and incident angle. Yet, deviations are observed at low energies, where surface binding energies and chemical effects become dominant, or at high energies, where nonlinear cascade effects emerge. For example, experimental studies on compound targets reveal preferential sputtering of lighter elements, a phenomenon not captured in early models but later incorporated into more advanced simulations. Similarly, surface analytical data provide benchmarks for validating theoretical models of surface evolution. The ripple patterns observed by AFM after oblique ion bombardment match predictions from the Bradley–Harper continuum model, though additional effects such as ion-induced viscous flow or redeposition often need to be included to achieve quantitative agreement. Plasma diagnostics also contribute to theory–experiment correlation by validating assumptions about ion fluxes and energy distributions. For instance, Langmuir probe and OES measurements in HiPIMS plasmas have confirmed the presence of dense ionized metal fluxes, consistent with models of self-sputtering and plasma recycling. Thus, the iterative interplay between theory and experiment continues to refine our understanding of sputtering. The integration of experimental diagnostics with computational models is now standard practice, enabling predictive control over sputtering processes for advanced applications.

1.8 Applications of Sputtering

Sputtering has evolved from a laboratory-scale technique for studying ion–solid interactions into a cornerstone of modern thin-film and nanomaterials processing. Its versatility arises from the capacity to deposit a wide range of materials—including metals, semiconductors, dielectrics, and complex oxides—with excellent control over film thickness, composition, and microstructure. This section explores the breadth of sputtering applications, spanning from conventional thin-film deposition in electronics to advanced roles in energy conversion, miniaturized devices, and emerging quantum technologies.

1.8.1 Thin-film Deposition in Semiconductors, Dielectrics, and Metals

The primary and most widespread application of sputtering lies in the deposition of thin films. In semiconductor technology, sputtered films form the basis of micro-electronic devices, memory structures, and integrated circuits. Aluminum, for example, has been traditionally deposited by DC magnetron sputtering to create interconnects due to its high conductivity and ease of processing [8]. In more advanced nodes, copper interconnects and barrier layers such as Ta, TiN, and W are routinely fabricated by sputtering. The reliability of sputtering for depositing these materials lies in its line-of-sight nature, compatibility with lithography-defined features, and ability to produce dense, adherent films. Beyond metals,

dielectrics such as SiO_2 , Al_2O_3 , and HfO_2 are sputtered to provide insulating and gate layers in transistors and capacitors [36]. The conformality of sputtered films is often improved by combining sputtering with ion-assisted deposition, ensuring stoichiometric control and minimal defect formation. Sputtering of ferroelectric oxides such as $\text{Pb}(\text{Zr,Ti})\text{O}_3$ (PZT) and BaTiO_3 has also enabled the commercialization of nonvolatile ferroelectric random-access memories (FeRAM) [37]. Semiconductor thin films such as amorphous silicon (a-Si), GaN, and ZnO are also accessible by RF or reactive sputtering, expanding the portfolio of electronic and optoelectronic devices fabricated by this method. Table 1.4 listed the examples of thin films deposited by sputtering in the semiconductor industry.

Table 1.4 Examples of thin films deposited by sputtering in the semiconductor industry.

Material/film	Sputtering mode	Application	Key advantages
Al (Aluminum)	DC magnetron sputtering	Metal interconnects and contact layers	High conductivity, good adhesion, compatible with Si; large-area uniform deposition
Ti (Titanium)	DC or RF sputtering	Adhesion/barrier layer between Si and Cu/Al	Excellent adhesion and diffusion barrier properties
TiN (Titanium nitride)	Reactive DC magnetron sputtering	Hard coating and diffusion barrier in Cu metallization	High hardness, chemical stability, good barrier performance
W (Tungsten)	DC magnetron sputtering	Gate electrode and via plug filling	Low resistivity, high melting point, good thermal stability
SiO_2 (Silicon dioxide)	RF magnetron sputtering	Dielectric and passivation layers	Excellent insulation, optical transparency, and film uniformity
Si_3N_4 (Silicon nitride)	RF reactive sputtering	Dielectric, diffusion barrier, and encapsulation layers	High dielectric strength and chemical inertness
ITO (Indium tin oxide)	RF or DC magnetron sputtering	Transparent conducting films for displays and sensors	High optical transparency and electrical conductivity
Ta (Tantalum)	DC magnetron sputtering	Barrier and adhesion layer for Cu interconnects	Strong adhesion, stable barrier properties, good conformality
Cu (Copper)	DC magnetron sputtering	Interconnect metallization	Low electrical resistivity, excellent conductivity for ULSI circuits
HfO_2 (Hafnium oxide)	RF magnetron sputtering	High-k dielectric in MOSFETs	High dielectric constant, good interface quality, CMOS compatibility

1.8.2 Optical Coatings and Transparent Conducting Oxides

Another major application of sputtering is the fabrication of optical coatings, ranging from antireflection layers to decorative finishes and functional optics. Because sputtering can produce films with controlled thickness on the nanometer scale, it is highly suited for interference coatings on glass and polymers. Dielectrics such as TiO_2 , Si_3N_4 , and MgF_2 are routinely sputtered to construct multilayer stacks with tailored refractive indices [38]. Transparent conducting oxides (TCOs) such as indium tin oxide (ITO), aluminum-doped ZnO (AZO), and fluorine-doped SnO_2 are almost exclusively deposited by sputtering in both research and industry [39]. Their dual functionality—high optical transparency and good electrical conductivity—makes them indispensable in displays, touch panels, and solar cells. Magnetron sputtering provides a scalable and reproducible method to produce TCO films with uniform thickness across large-area substrates, a requirement for flat-panel display and photovoltaic (PV) manufacturing. Recent progress in reactive sputtering has expanded the scope of optical coatings, enabling the preparation of nitride- and oxide-based films with superior durability and tailored bandgaps [40]. HiPIMS has further improved the quality of optical coatings, producing dense films with minimal defects and enhanced adhesion to substrates [41].

1.8.3 Nanostructuring and Surface Modification

Sputtering is not limited to thin-film deposition; it also serves as a versatile tool for nanostructuring and modifying surfaces. By carefully tuning deposition parameters such as pressure, substrate bias, and power, films with tailored porosity, columnar structures, or nanopatterned morphologies can be achieved [42]. These structures are particularly relevant for catalysis, plasmonics, and sensor technologies, where surface area and nanoscale ordering dictate functionality. In ion beam sputtering and glancing angle deposition (GLAD), directional fluxes of sputtered atoms are exploited to engineer nanorods, nanopillars, and helical structures [43]. These nanostructures exhibit unique optical and mechanical properties, enabling applications in photonic crystals, biosensors, and superhydrophobic coatings. Surface modification via sputtering also includes doping of substrates with foreign atoms, creation of self-cleaning or antimicrobial surfaces, and texturing to enhance adhesion or wettability. Another significant application is the production of hard coatings such as TiN, CrN, and DLC. These coatings, fabricated by reactive sputtering, are widely used in cutting tools, biomedical implants, and protective layers in consumer devices due to their high hardness, low friction, and chemical stability [44].

1.8.4 Microelectromechanical System and Nanoelectromechanical System Devices

Microelectromechanical systems (MEMS) and nanoelectromechanical systems (NEMS) represent another field where sputtering plays a crucial role. These devices, which integrate mechanical and electrical functions at small scales, require thin

films with precise thickness control, stress management, and compatibility with silicon processing. Sputtering enables deposition of structural layers (e.g., polysilicon, metals), sacrificial layers, and functional coatings such as piezoelectrics and conductors [45]. Aluminum and gold films deposited by sputtering are frequently used for interconnects in MEMS. Piezoelectric films such as AlN and ZnO are sputtered to fabricate resonators, filters, and sensors [46]. Moreover, multilayer stacks of ferroelectric materials are sputtered to achieve high-performance actuators and energy harvesters in MEMS/NEMS platforms. The compatibility of sputtering with lithography-based patterning and wafer-scale processing makes it indispensable in commercial MEMS fabrication lines.

1.8.5 Energy Applications: PV, Batteries, and Fuel Cells

Sputtering is extensively applied in the energy sector, particularly in PV, batteries, and fuel cells. In thin-film solar cells, TCOs deposited by sputtering serve as transparent electrodes, while absorber layers such as CdS, ZnO, and Cu(In,Ga)Se₂ are prepared using reactive or cosputtering [47]. The ability to deposit multilayer heterostructures with precise stoichiometry is critical for maximizing PV efficiency. For example, sputtered ZnO:Al films provide superior transparency and conductivity in tandem solar cells [48]. In lithium-ion batteries, sputtered thin films of LiCoO₂, LiPON (lithium phosphorus oxynitride), and transition metal oxides are employed in solid-state microbatteries [49]. These films act as cathodes, electrolytes, or protective coatings, enabling long cycle life and safety in miniaturized energy-storage devices. Similarly, sputtering of solid oxide fuel cell components, such as yttria-stabilized zirconia (YSZ) electrolytes and perovskite electrodes, enhances cell efficiency and mechanical durability [50]. The recent push toward hydrogen economy has also highlighted sputtering as a method to deposit catalysts for hydrogen evolution and storage, particularly Pt-based nanostructures with tailored morphology [51]. This intersection of energy materials and sputtering underscores its critical role in sustainable technologies.

1.8.6 Emerging Applications in Quantum Devices and Spintronics

The frontier of sputtering applications is found in quantum technologies and spintronics. In spintronic devices, materials such as magnetic tunnel junctions (MTJs), Heusler alloys, and multiferroic oxides are sputtered to form nanoscale heterostructures that exploit electron spin in addition to charge [52]. Sputtered CoFeB/MgO/CoFeB trilayers, for instance, form the backbone of modern magnetic random-access memory (MRAM), offering nonvolatility, high speed, and scalability [53]. Figure 1.8 shows the schematic of the fabricated MTJs using sputtering. Quantum devices, including superconducting qubits and topological insulators, also rely on sputtering to deposit high-purity films with controlled interfaces. Nb, Al, and NbN films deposited by sputtering are used as superconducting layers in Josephson junctions and quantum circuits [54]. Furthermore, reactive sputtering enables the preparation of nitride-based superconductors and hybrid materials, essential for next-generation




Figure 1.8 Schematic of the fabricated MTJs. (a)–(c) A SyF free layer is sandwiched by asymmetric double MgO barriers. The bottom electrode is Ta or W, and the top electrode is Ta/Pt. The Co₂FeAl and CoFeB thicknesses in the SyF free layer varied from 0.5 to 1.5 nm for each stack by wedge across the wafer. *Source:* Reproduced from [56] / with permission of IOP Publishing.

quantum computing architectures. Sputtering has also been applied in producing 2D materials and layered heterostructures, which are increasingly investigated for quantum sensing. For instance, sputtered transition metal dichalcogenides (TMDs) like MoS₂ can be integrated with conventional semiconductors for hybrid quantum devices [55].

1.9 Challenges and Future Perspectives

Sputtering, being the versatile and widely adopted technique for thin-film deposition and surface modification, lays at the heart of modern materials science. Despite its maturity and broad applications, sputtering is still plagued by fundamental and practical limitations that preclude it from reaching its full potential. These problems cover everything from theoretical bounds to material-specific constraints, process scalability, and integration issues with emerging technologies. Nowadays, within the available theoretical models, such as Sigmund's collision cascade theory and Monte Carlo simulations like TRIM/SRIM, the predictability of sputtering behavior in complex alloys, oxides, or nanostructured material remains limited, while MD approaches are computationally demanding. A second important issue deals with the control of defects and stoichiometry: point defects, vacancies, and compositional deviations affect film properties, in particular in reactive sputtering, where target poisoning and plasma nonuniformity may occur. Advanced methods such as HiPIMS improve film density and smoothness, but real-time diagnostics and feedback control remain crucial for precise film engineering. At the industrial scale, sputtering requires uniform large-area deposition, high efficiency, and optimized power consumption—all needs to which hybrid magnetron and pulsed systems start to answer. Integration with state-of-the-art fabrication techniques like ALD, CVD, and additive manufacturing not only opens up perspectives toward multifunctional coatings but also implies synchronization to avoid interface defects and thermal mismatch. Emerging applications

in the field of quantum materials and spintronics push sputtering toward atomic-level precision, putting high demands on plasma control and integration within *in situ* characterization and machine-learning-based process optimization. Lastly, environmental sustainability nowadays urges the development of low-energy, gas-efficient, recyclable sputtering systems. Overcoming these challenges through interdisciplinary research will make sputtering continue to be one of the key techniques for the fabrication of next-generation materials and devices.

1.10 Conclusion

Sputtering has evolved into one of the most versatile and indispensable methods in modern materials science, as it bridges between fundamental ion–solid interaction physics and practical thin-film applications. The method is defined by complex processes like collision cascades, momentum transfer, and secondary emissions, allowing great precision in film composition, thickness, and morphology. Advanced variants, including magnetron, RF, reactive, and HiPIMS, have considerably expanded its capability to deposit metals, dielectrics, semiconductors, and multicomponent materials with excellent uniformity and adhesion. The technique has played a very important role in micro- and optoelectronics, protective coatings, and nanostructured surface engineering and finds emerging applications in MEMS/NEMS, energy devices, spintronics, and quantum materials. Still, predictive modeling and defect/stoichiometry control and large-scale process optimization are among a few challenges lying ahead. Integration with complementary methods like atomic layer deposition or additive manufacturing provides pathways to overcome such limitations and realize hybrid, multifunctional material systems. Given the advancement of technological frontiers toward nanoscale precision and sustainable manufacturing, sputtering will keep acting as one of the key platforms for materials innovation, linking scientific understanding to practical device realization.

References

- 1 Sigmund, P. (1990). Theory of sputtering. I. Sputtering yield of amorphous and polycrystalline targets. *Physical Review* 184(1969): 383–416.
- 2 Yamamura, Y. and Tawara, H. (1996). Energy dependence of ion-induced sputtering yields from monatomic solids at normal incidence. *Atomic Data and Nuclear Data Tables* 62: 149–253.
- 3 Grove, W.R. (1852). On the electro-chemical polarity of gases. *Philosophical Transactions of the Royal Society of London* 142: 87–101.
- 4 Behrisch, R. (Ed.) (1981). *Sputtering by Particle Bombardment I*. Springer.
- 5 Chapman, B. (1980). *Glow Discharge Processes: Sputtering and Plasma Etching*. Wiley-Interscience.
- 6 Kelly, P.J. and Arnell, R.D. (2000). Magnetron sputtering: A review of recent developments. *Vacuum* 56: 159–172.

- 7 Gudmundsson, J.T., Brenning, N., Lundin, D. et al. (2012). High power impulse magnetron sputtering discharge. *Journal of Vacuum Science & Technology A* 30: 030801.
- 8 Mattox, D.M. (2010). *Handbook of Physical Vapor Deposition (PVD) Processing*. Elsevier.
- 9 Behrisch, R. and Eckstein, W. (Eds.) (2007). *Sputtering by Particle Bombardment: Experiments and Computer Calculations from Threshold to MeV Energies*. Springer.
- 10 Schiller, S. and Heisig, U. (2003). *Magnetron Sputtering and Applications*. Surface Engineering Series.
- 11 Murray, C.B., Norris, D.J., and Bawendi, M.G. (2011). Nanostructured materials for energy conversion. *Science* 331: 199–203.
- 12 Ziegler, J.F., Ziegler, M.D., and Biersack, J.P. (2010). SRIM – The stopping and range of ions in matter. *Nuclear Instruments and Methods in Physics Research Section B* 268: 1818–1823.
- 13 Anders, A. (2010). *Physics of Sputtering and Plasma-Based Thin Film Deposition*. Springer.
- 14 Thompson, M.W. (1968). The energy spectrum of ejected atoms during the high energy sputtering of metals. *Philosophical Magazine* 18: 377–414.
- 15 Ohring, M. (2002). *Materials Science of Thin Films: Deposition and Structure*. Academic Press.
- 16 Rossmagel, S.M. and Cuomo, J.J. (1985). Magnetron sputter deposition. *Annual Review of Materials Science* 15: 387–425.
- 17 Penfold, J. and Thornton, J.A. (1976). RF sputtering of insulating oxides. *Journal of Vacuum Science and Technology* 13: 970–975.
- 18 Bunshah, R.F. (1994). *Handbook of Deposition Technologies for Films and Coatings*. Noyes Publications.
- 19 Gudmundsson, J.T. (2008). High power impulse magnetron sputtering. *Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films* 26: 531–540.
- 20 Yamamura, Y. (1983). Angular dependence of sputtering yields of monatomic solids. *Nuclear Instruments and Methods in Physics Research* 194: 515–522.
- 21 Ziegler, J.F., Biersack, J.P., and Littmark, U. (1985). *The Stopping and Range of Ions in Solids*. Pergamon Press.
- 22 Möller, W. and Eckstein, W. (2010). SDTrimSP: A Monte-Carlo code for sputtering, ion implantation and atomic transport. *Nuclear Instruments and Methods in Physics Research Section B* 268: 1833–1838.
- 23 Robinson, M.T. and Torrens, I.M. (1974). Computer simulation of atomic-displacement cascades in solids in the binary-collision approximation. *Physical Review B* 9: 5008–5024.
- 24 Nordlund, K., Keinonen, J., and Mattila, T. (1998). Formation of ion irradiation induced small-scale defects on surfaces. *Physical Review Letters* 77: 699–702.
- 25 Bringa, E.M. and Johnson, R.E. (2002). Molecular dynamics and Monte Carlo simulations of cluster bombardment. *Nuclear Instruments and Methods in Physics Research Section B* 193: 365–370.
- 26 Sigmund, P. and Gras-Marti, A. (1981). Theoretical aspects of atomic mixing by ion beams, *Nuclear Instruments and Methods*, 182–183: 2541.

- 27 Zhou, X., Bartels, C., Nordlund, K. et al. (2020). Machine-learning interatomic potentials for ion–solid interactions, *Journal of Applied Physics* 128: 225902.
- 28 Eckstein, W. (2007). *Computer Simulation of Ion-Solid Interactions*. Springer.
- 29 Matsunami, N., Yamamura, Y., Itikawa, Y. et al. (1984). Energy dependence of ion-induced sputtering yields of monatomic solids. *Atomic Data and Nuclear Data Tables* 31: 1–80.
- 30 Benninghoven, A., Rüdenauer, F.G., and Werner, H.W. (1987). *Secondary Ion Mass Spectrometry: Basic Concepts, Instrumental Aspects, Applications, and Trends*. Wiley.
- 31 Facsko, S., Dekorsy, T., Koerd, C. et al. (1999). Self-organized pattern formation on semiconductor surfaces by ion beam erosion. *Science* 285: 1551–1553.
- 32 Sulania, I., Sondhi, H., Kumar, T. et al. (2024). Investigating ripple pattern formation and damage profiles in Si and Ge induced by 100 keV Ar⁺ ion beam: A comparative study. *Beilstein Journal of Nanotechnology* 15: 367–375.
- 33 Berg, S. and Nyberg, T. (2005). Fundamental understanding and modeling of reactive sputtering processes. *Thin Solid Films* 476: 215–230.
- 34 Window, B. and Savvides, N. (1986). Unbalanced magnetrons as sources of high ion fluxes. *Journal of Vacuum Science & Technology A* 4: 453–456.
- 35 Anders, A. (2000). *Handbook of Plasma Immersion Ion Implantation and Deposition*. Wiley.
- 36 Robertson, J. (2006). High dielectric constant oxides. *European Physical Journal - Applied Physics* 28: 265–291.
- 37 Scott, J.F. (2007). Applications of modern ferroelectrics, *Science* 315: 954–959.
- 38 Pulker, H.K. (1999). *Coatings on Glass*, Elsevier.
- 39 Granqvist, C.G. (2007). Transparent conductors as solar energy materials: A panoramic review. *Solar Energy Materials & Solar Cells* 91: 1529–1598.
- 40 Martin, P.M. (2010). *Handbook of Deposition Technologies for Films and Coatings*, 3rd ed. William Andrew.
- 41 Anders, A. (2017). A review comparing cathodic arcs and high-power impulse magnetron sputtering (HiPIMS). *Surface and Coatings Technology* 322: 190–201.
- 42 Mahieu, S. and Depla, D. (2009). Reactive sputter deposition of TiN layers: Modelling the growth by characterization of the particle flux. *Journal of Physics D: Applied Physics* 42: 053002.
- 43 Barranco, A., Borrás, A., Gonzalez-Elipe, A.R. et al. (2016). Perspectives on oblique angle deposition of thin films: From fundamentals to devices. *Progress in Materials Science* 76: 59–153.
- 44 Holmberg, K. and Matthews, A. (2009). *Coatings Tribology: Properties, Mechanisms, Techniques and Applications in Surface Engineering*. Elsevier.
- 45 Senturia, S.D. (2001). *Microsystem Design*. Springer.
- 46 Wingqvist, G. (2010). Sputtered thin film acoustic wave resonators. *Vacuum* 84: 883–890.
- 47 Green, M.A. (2019). Commercial progress and challenges for photovoltaics. *Nature Energy* 4: 12–17.
- 48 Ellmer, K. (2012). Past achievements and future challenges in the development of optically transparent electrodes. *Nature Photonics* 6: 809–817.

- 49 Bates, J.B., Dudney, N.J., Lubben, D. et al. (2000). Thin-film lithium and lithium-ion batteries. *Solid State Ionics* 135: 33–45.
- 50 Gorte, R.J. and Vohs, J.M. (2003). Nanostructured anodes for solid oxide fuel cells. *Current Opinion in Colloid & Interface Science* 8: 212–219.
- 51 Sun, K., Shen, S., Liang, Y. et al. (2017). Sputtered platinum thin films as efficient electrocatalysts for hydrogen evolution reaction. *Journal of Power Sources* 364: 395–403.
- 52 Chappert, C., Fert, A., and Van Dau, F.N. (2007). The emergence of spin electronics in data storage. *Nature Materials* 6: 813–823.
- 53 Ikeda, S., Miura, K., Yamamoto, H. et al. (2010). A perpendicular-anisotropy CoFeB–MgO magnetic tunnel junction. *Nature Materials* 9 (2010): 721–724.
- 54 Oliver, W.D. and Welander, P.B. (2013). Materials in superconducting quantum bits. *MRS Bulletin* 38: 816–825.
- 55 Chhowalla, M., Shin, H.S., Eda, G. et al. (2013). The chemistry of two-dimensional layered transition metal dichalcogenide nanosheets. *Nature Chemistry* 5: 263–275.
- 56 Grezes, C., Li, X., Wong, K. et al. (2020). Voltage-controlled magnetic tunnel junctions with synthetic ferromagnet free layers sandwiched by asymmetric double MgO barriers. *Journal of Physics D: Applied Physics* 53: 014006.

